

Lignodur Hydrodol 240



Wood oil treatment based on linseed oil



www.blauer-engel.de/uz12a

Field of application

For treatments or decorative coatings of wooden elements and surfaces. Can be used as a transparent one-pot system for non-dimensionally stable and limited dimensionally stable wooden components. Can be used on wooden paneling and furniture, panels, fences, balconies and terraces.

Properties

- water-based wood oil
- for indoors and outdoors
- based on natural linseed oil
- matt
- excellent penetration behavior
- cures quickly
- pearling effect
- moisture regulating

Material description

Color shades	Scale no.	Description
	-	0100 transparent ¹⁾
	06.OL.08	1409 light oak
	12.OL.05	8412 teak
	12.OL.07	8408 bangkirai
	15.OL.13	8409 nut
	15.OL.04	1412 larch
	15.OL.12	1413 douglas fir
	75.OL.02	7411 graphite

¹⁾ may only be used in combination, please refer to the information below Notes

Material description

Gloss grade	Matt
Base material	Modified, natural linseed oils, pigmented
Constituent substances	Alkyd resin emulsion based on linseed oil, titan dioxide (depending on the color shade), organic or inorganic colored pigments (depending on the color shade), water, glycol ether, additives, preservatives (benzisothiazolinone and zinc pyrithione)
VOC	EU limit for this product (Cat. A/e): 130 g/l (2010). This product contains max. 30 g/l VOC.
Density	Approx. 1.0–1.1 g/cm ³ , depending on the color shade.
Packaging	750 ml, 3 l and 10 l

Use

Thinning	Ready for application.
Tinting	All colors can be mixed with one another without limitations.
Compatibility	Do not mix with other types of materials.
Application	Stir thoroughly before use. Evenly apply Lignodur Hydrodol 240 with the Uni-Plus-Paint Brush 1212 or the Uni-Plus Whitewash Brush 1211 in a thin film parallel to the grain and thoroughly distribute it. For first coats, if possible, treat the wood on all sides (for terrace planks, e.g. before installation). After drying, quickly apply another thin second coat. Excessive layer thickness and poor ventilation lead to delays in drying.
Consumption	Approx. 70–90 ml/m ² per layer. Determine the exact consumption by means of a test application on the object to be coated.
Application temperature	Do not apply if the air and object temperature is below +5°C or above +30°C.
Tool cleaning	Clean tools immediately after use with water and soap.

Drying (+20°C, 65% relative humidity)

Recoat after approx. 12 hours. Fully stressable after approx. 5 days. Allow for longer drying time if the temperature is lower and/or the humidity is higher.

Storage

Store in a cool, dry and frost-free place. Reseal opened containers tightly and use the contents as soon as possible. Only recycle completely empty containers. Dispose of liquid material residue at a collection point for old paint.

Declaration

Product code	Ö20+ Comply with the specifications in the current safety data sheet. Contains benzisothiazolinone and zinc pyrithion. Can cause allergic reactions. Allergy information at +49 251 7188-403.
---------------------	--

Coating build-up

Substrate preparation

The substrate must be absorbent, solid, dry, clean, load-bearing and free from separating agents. The BFS Leaflet no. 18 specifies that the moisture content for non-dimensionally stable components and components with limited dimensional stability, the moisture content must not exceed 18%. Lightly sand and clean new, especially planed wooden surfaces. Carefully remove all sanding dust. To prevent discolorations, allow new tannic-rich woods (e.g. douglas fir, larch) to weather for 2–3 weeks before thoroughly cleaning them with Wood Degrayer 1024. Clean grayed and soiled wooden surfaces as well as wooden surfaces affected by tannic-induced stains with Wood Degrayer 1024. Old paint coatings must be completely removed. Hazardous particles and vapors may be released while reworking or removing old paint coats, e.g. as a result of sanding, paint removal by heat gun, etc.

Prime coats, intermediate coats and top coats

With Lignodur Hydrodol 240 in the desired color shade. As a first coat on new, untreated woods, apply at least two coats. In outdoor areas exposed to weathering, apply three coats depending on the absorbency of the wood and the selected color shade. When retreating or for renovation coats, depending on the requirements, apply 1–2 coats.

Notes

Protective measures

Keep out of reach of children. Use the Dust Filter P2 during sanding. Ensure proper ventilation during application and drying. Avoid eating, drinking and smoking during application. Upon contact with eyes or skin, immediately rinse thoroughly with water. Ensure that the material does not enter the sewage system, waters or soil.

Sand the substrates

We recommend sanding the surfaces between the individual work steps. Carefully remove all sanding dust.

Assess the color shade

The various kinds of wood and available intact coatings affect the color shade due to intrinsic color and absorbency. For this reason, we recommend applying a test coat in advance. Wood oils strengthen the natural color shade of the timber.

Colorless build-up outdoors

Colorless coats are not suitable as a sole coating build-up for use in exterior areas due to their insufficient UV protection.

Constituent-rich wood

In constituent-rich woods such as oak, red cedar, afzelia or redwood, rain can cause water-based wood constituents to bleed out.

Application indoors

For large-scale applications indoors (e.g. on ceilings and walls), we recommend using the water-based woodstain Lignodur Grenodecor 236 (due to the typical odor of Lignodur Hydrodol 240). Please contact the Brillux Consulting Service if you require assistance in this context.

Not suitable for interior surfaces of furniture

Do not treat the interior surfaces of furniture and cabinets due to possible odors.

Factory-treated wood

When wood has already been treated in the factory, observe the product information, care instructions and manufacturer regulations before use.

Notes

Care and maintenance Regularly check the conditions of wooden areas outdoors, especially when exposed to weathering, and conduct appropriate renovations. For areas exposed to weathering, an annual treatment coat is usually necessary.

Further information Follow the instructions on the data sheets of the products used.

Remark

This data sheet is based on extensive development work and years of practical experience. The translation corresponds to the current German version, in compliance with the German laws, regulations, standards and guidelines. Its content does not constitute a contractual legal relationship. The user/buyer is not released from the responsibility of checking our products to ensure they are suitable for the intended application. In addition, our general terms of business apply.

When a new version of this data sheet with updated information is published, the previous version no longer applies. The current version is available on our website.

Brillux
Weseler Straße 401
48163 Münster
GERMANY
Phone +49 251 7188-0
Fax +49 251 7188-105
info@brillux.de
www.brillux.com