### **Data Sheet**

# Sensocryl 267

Low-emission, solvent and plasticizer-free premium wall finish with pure acrylate bonding agent, water-dilutable, wet abrasion resistance: R class 1, disinfectant-resistant, cleanable, silk matt, for interior use









**Color System** 

### Field of application

For hard-wearing interior ceiling and wall coatings with good flow properties. Especially for smooth or textured wall coverings such as CreaGlas Fabric, Relief 3490, CreaGlas Nonwoven, Rapid Nonwoven, woodchip wallpaper, foam vinyl or embossed wallpaper. Also on load-bearing substrates, such as interior plaster, concrete, gypsum plasterboard, etc. Particularly suitable for use in demanding areas such as in hospitals, medical practices, schools, childcare centers, hotels, canteens, office buildings and in high-end private living spaces.

### **Properties**

- For interior use
- Low-emission, solvent- and plasticizer-free
- Free of fogging-active substances
- Suitable for indirect contact with foodstuffs in accordance with the test certificate
- Silk matt
- Very hard-wearing
- Very bright white color shade
- Very vibrant color shades
- Resistant to watery, non-alcohol-based disinfectant in accordance with the test certificate
- Excellent cleanability
- Schwerentflammbar B1 (flame-retardant) in system build-up with CreaGlas fabric / nonwoven, Relief 3490 and nonwoven wall coverings in accordance with the test certificate
- Water-vapor-permeable
- Also suitable for use in clean rooms in the gloss grade silk matt
- Very easy to apply

### **Material description**

Color shades 0095 white

Additional color shades can be mixed with the Brillux Color System.

Base material Pure acrylate

**Density** Approx. 1.3–1.4 g/cm<sup>3</sup>



Page 1 of 5 Data Sheet 267 en Date: 27.06.2023

**Material description** 

Classified in accordance with

**ance with** Wet abrasion resistance: R class 1 **EN 13300** Contrast ratio: H<sub>10</sub> class 2 (at 7 m²/l)

Gloss: G2b medium glossy (silk matt)

Maximum grain size: S1 fine

Reaction to fire A2 – s1,d0 in accordance with DIN EN 13501-1 ("nichtbrennbar" non-

combustible)

In system build-up with Briplast filler material according to classification

report no. 230010838-3

B1 - in accordance with DIN 4102 ("schwerentflammbar" flame-

retardant)

In system build-up with CreaGlas fabric / nonwoven, Relief 3490 and nonwoven wall coverings in accordance with the test certificate

Packaging 0095 white: 5 l, 15 l

Color System: 5 I, 15 I

Use

**Thinning** As required, especially for low-texture application on smooth substrates,

e.g. nonwoven, dilute slightly with water.

**Tinting** Up to max. 10% with Full Color and Tinting Paint 951.

Compatibility Can only be mixed with materials of the same type and those specified

in this data sheet.

**Application** Sensocryl 267 can be applied by using a brush, roller or airless spray

application.

**Consumption** Approx. 130 to 150 ml/m² per coat on smooth substrates.

In system build-up with CreaGlas Fabric approx. 170-230 ml/m² for the

intermediate coat and approx. 130-150 ml/m² for the final coat.

Determine the exact consumption by means of a test application on the

object to be coated.

**Application temperature** Do not apply if air or object temperature is below +5°C.

**Tool cleaning** Clean tools with water immediately after use.

### Spray data

Spray system	Nozzle	Spray angle	Pressure	Thinning
Airless	0.021–0.027 inch	40°–80°	150 bar	Approx. 5%

### Drying (+20°C, 65% relative humidity)

Surface dry and recoatable after approx. 4–6 hours. On larger surfaces, the drying time between application of the individual coats should be at least 12 hours.

Allow longer drying times at lower temperatures and/or higher air humidity.



Store in a cool and frost-free place. Reseal opened containers tightly.

Declaration

Notes Contains preservatives.

Do not inhale spray mist.

Product code BSW20

Comply with the specifications in the current safety data sheet.

### Coating build-up

### Substrate preparation

The substrate must be solid, dry, clean, load-bearing and free from efflorescence, sinter layers, separating agents, corrosion-promoting components or other intermediate layers affecting the adhesion. Check the suitability, load-bearing capacity and adhesive properties of existing coatings. Thoroughly remove defective and unsuitable coatings and dispose of them in accordance with the applicable regulations. Thoroughly rinse off reversible, water-sensitive coats (e.g. distemper). Wash down intact coats of oil paints and enamels with an alkaline solution, sand well and clean. Completely remove any wall coverings that are not suitable for painting; this includes any paste or wall-glue residue. Treat replastered areas with a fluorine primer; if the subsequent paint coat is to be tinted, prime the entire surface. Apply a prime and/or intermediate coat to the substrate as required. See also VOB Part C, DIN 18363, Section 3.

#### First coats

Substrates	Prime coat	Intermediate coat	Top coat
Interior plaster (depending on the compressive strength <sup>1)</sup> ), concrete	If necessary, Lacryl Deep Penetrating Primer 595, Deep Penetrating Primer 545 or Adhesion Primer 3720, Wall Primer 3729 or Wall Primer Coarse 3728		
Gypsum plaster <sup>1)</sup> , gypsum plasterboard <sup>2)</sup> , gypsum plasterboard panels	Depending on the individual requirements With Lacryl Deep Penetrating Primer 595, Lacryl Hydro-Gel 695 or Wall Primer 3729	1–2x Sensocryl 267	Sensocryl 267
Wall coverings, e.g. woodchip wallpaper, CreaGlas fabric / nonwoven, rapid nonwoven, nonwoven wall coverings, embossed wallpaper			

<sup>&</sup>lt;sup>1)</sup> Minimum compressive strength> 2.0 N/mm² (Compressive strength class CS II, CS III, CS IV as well as B1–B7)



<sup>&</sup>lt;sup>2)</sup> Prime soft and highly absorbent filler zones and substrates with Lacryl Deep Penetrating Primer 595 as part of the substrate pre-treatment.

### Coating build-up

### **Renovation coats**

Substrates	Prime coat	Intermediate coat	Top coat	
Normally absorbent substrates, e.g. matt emulsion paint coats	If necessary, Lacryl Deep Penetrating Primer 595 or Adhesion Primer 3720			
Non or not very absorbent substrates, e.g. oil and varnish coatings, glossy emulsion paint coatings	Adhesion Primer 3720	depending on the situation on site and the individual requirements Sensocryl 267	Sensocryl 267	
Intact, two-component coating, e.g. CreaGlas 2K-PU Finish	2K-Aqua EP Primer 2373			

### Assessment of cleanability according to the test report

Medium	Conventional interior emulsion paint	Sensocryl 266 matt	Sensocryl 267 silk matt	Sensocryl 268 silk gloss	Sensocryl 269 gloss
Cola	Significant trace 2)	OK, minimum residue	OK 1)	OK 1)	OK 1)
Orange juice	Heavy trace 3)	Minor residue	OK 1)	OK 1)	OK 1)
Instant coffee	Heavy trace 3)	OK 1)	OK 1)	OK 1)	OK 1)
Strawberry jam	Significant trace 2)	OK, minimum residue	OK 1)	OK 1)	OK 1)

<sup>1)</sup> No residue after cleaning

### Notes

# Hairline-crack-bridging coating on gypsum plasterboard

Hairline-crack-bridging coating on, e.g., gypsum plasterboard, gypsum fiber boards or similar substrates, in accordance with VOB Part C, DIN 18363, para. 3.2.1.2, can be achieved with full-surface reinforcement with, e.g., nonwoven wall coverings based on cellulose and fiberglass.

## Discolorations on gypsum plasterboard

An additional sealing coating must be applied if there is a risk of discolorations bleeding through the untreated gypsum plasterboard. Depending on the situation on site, use Aqualoma 202, Isolating Primer 924 or CreaGlas 2K-PU-Finish 3471. For an accurate assessment, sample coatings of various panel widths, including the joints and filled areas, have proved to be useful.

### Filling rough surfaces

Smooth rough surfaces before the coating build-up by filling them with, e.g., Briplast Silafill 1886, as required.



<sup>&</sup>lt;sup>2)</sup> Significant traces following cleaning involving characteristics that are visible and can be felt.

<sup>3)</sup> Heavy traces following cleaning involving unreasonable characteristics that are visible and can be felt.

### Notes

### Priming gypsum plaster

For gypsum-based plasters with strong absorbency, sufficient stabilization is not always achieved. We recommend testing the adhesion of the complete coating build-up with an adhesive tape test (e.g. Tesa Precision Masking Tape, Gold 4334) to ensure a reliable assessment. Where appropriate, implement priming with Deep Penetrating Primer.

### Brilliant and intense color shades

Brilliant, pure intense color shades, e.g. in the yellow, orange, red, magenta and yellow-green range, have a low hiding power due to the nature of their pigments. When using critical color shades in these color ranges, we recommend applying a full-covering prime coat in the corresponding base color (Basecode). In addition to the standard coating buildup, additional coats may be required.

# Compatibility with sealing compounds

When coating sealing compounds, e.g., acrylic sealing materials, due to higher elasticity, cracks, can occur in the coating material. This may also cause discoloration in the coating. Due to the wide variety of sealing systems on the market, it is vital to perform tests for each individual case to assess the adhesion and application result.

### Touch-ups

Touch-ups to part of a surface are always visible. The degree to which they stand out depends on the situation on site. According to BFS Leaflet no. 25, Section 4.2.2.1, Paragraph e, this is unavoidable.

#### Use of disinfectants

In addition to the disinfectants listed in the test report, others may also be assessed for suitability. Contact the Brillux Consulting Service for more information.

### Thin layers on smooth substrates

For thin-layer application to create low-texture surfaces on smooth substrates (e.g. filled gypsum plasterboard), additional coats may be required in order to achieve sufficient coverage or other measures may be required in the coating build-up. If necessary, contact the Brillux Consulting Service.

### **Further information**

Follow the instructions in the data sheets of the products used and for the different CreaGlas Fabric types.

### Remark

This data sheet is based on extensive development work and years of practical experience. The translation corresponds to the current German version, in compliance with the German laws, regulations, standards and guidelines. Its content does not constitute a contractual legal relationship. The user/buyer is not released from the responsibility of checking our products to ensure they are suitable for the intended application. In addition, our general terms of business apply.

When a new version of this data sheet with updated information is published, the previous version no longer applies. The current version is available on our website.

Brillux Weseler Straße 401 48163 Münster GERMANY Phone +49 251 7188-0 Fax +49 251 7188-105 info@brillux.de www.brillux.com

