### **Data Sheet**

## **Adhesion Primer 3720**

Haftgrund 3720

Low-emission, solvent- and plasticizer-free, pigmented, low-odor, adhesion-promoting, for indoors and outdoors







#### Field of application

Can be used as an adhesion promoter and primer for subsequent paint coats and coatings on non-absorbent or low-absorbent substrates, e.g. exterior and interior plaster, concrete and on firmly-adhesive, load-bearing old coats, e.g. emulsion paint coats, polymerized resin, oil or enamel coats or glossy emulsions. Can also be used as contact coating for dispersion silicate paints on non-silicificating substrates, e.g. old emulsion paint coats. Also for use as a prime and/or intermediate coat for higher demands of the surface finish and for intense colored top coats, especially for example on smooth surfaces or surfaces with incidence of grazing light.

#### **Properties**

- low emission, solvent- and plasticizer-free
- Water-dilutable
- For interior and exterior use
- Weather-resistant
- Low odor
- Water-vapor-permeable
- Adhesion promoting
- Stabilizing
- Extends the open time of subsequent coatings
- Optionally available for use on exterior components in Protect quality (film protection against an algal and fungal infestation of the coating)

#### **Material description**

Color shades 0095 white

Basecode color shades and light to medium color shades can be mixed with the Brillux Color System. Additional color shades available upon request.

Gloss grade Matt

Base material Styrene-acrylic-copolymer

en Date: 29.06.2023



#### **Material description**

Density Approx. 1,35–1,45 g/cm<sup>3</sup>

Packaging 0095 white: 5 l, 15 l

Color System: 5 I, 15 I

Use

**Thinning** If necessary, thin slightly with water.

**Tinting** Up to max. 10% with Full Color and Tinting Paint 951.

**Application** Adhesion Primer 3720 can be applied with a brush, roller or airless

spraying.

Consumption Approx. 150 to 200 ml/m² per coat on smooth substrates. Consumption

increases on rough surfaces accordingly.

Determine the exact consumption by means of a test application on the

object to be coated.

**Application temperature** Do not apply if air or object temperature is below +5°C.

**Tool cleaning** Clean tools with water immediately after use.

#### Spray data

Spray system	Nozzle	Jet angle	Pressure	Thinning
Airless	0.021–0.017 inch	40°–80°	150 bar	Approx. 5%

#### Drying (+20°C, 65% relative humidity)

Rainproof after approx. 4 hours. Suitable for recoating and additional

system build-up after approx. 12 hours.

Allow longer drying times at lower temperatures and/or higher air

humidity.

#### Storage

Store in a cool and frost-free place. Reseal opened containers tightly.

#### Declaration

**Notes** Contains preservatives.

Do not inhale spray mist.

Product code BSW20

Comply with the specifications in the current safety data sheet.



#### Coating build-up

#### Substrate preparation

The substrate must be solid, dry, clean, load-bearing, free from efflorescence, sinter layers, separating agents, corrosion-promoting components or other intermediate layers affecting the adhesion. Check existing coatings for their suitability, load-bearing capacity and adhesive properties. Remove non-bearing and unsuitable coats and dispose of them as per the applicable regulations. Thoroughly rinse off reversible, water-sensitive coats (e.g. limepaint). Wash down intact coats of oil paints and varnishes with an alkaline solution, sand down well and clean. Clean surfaces infested with fungi and algae thoroughly and then treat them with Universal Disinfectant 542\*. (\* Use biocide products with care. Always read the label and product information before use.) Treat replastered areas with a fluorine primer. Repair damaged concrete using materials from the Brillux concrete protection system. Also see VOB Part C, DIN 18363, Section 3.

#### Coating build-up

Substrates 2)	Prime coat	Top coat
Gloss or non-absorbent and low- absorbent substrates, e.g., interior or exterior plaster (depending on the compressive strength <sup>1)</sup> ), concrete, emulsion, polymerized resin or enamel coatings	Adhesion Primer 3720	Depending on the selection, further system build-up with e.g. emulsion paints and plastic materials

<sup>1)</sup> Minimum compressive strength > 2.0 N/mm² (compressive strength category CS II, CS III, CS IV)

#### Notes

# When applying gypsum-based hydraulic-setting filling materials

Do not use Adhesion Primer 3720 for subsequent plastering work with gypsum-based, hydraulic-setting filling materials, e.g. Briplast Prefill 143 or Briplast Planofill 1875. When using these fillers, we recommend Multiprimer LF 3084 is used as an adhesion promoting primer.

#### **Protect quality**

Containers marked with "Protect" contain material that is optimized in the factory with film preservation against algal and fungal infestation. The material may only be used outdoors. The contained preservatives minimize and/or delay the risk of algal and fungal attack. The material enhanced by adding film preservation must be applied with sufficient layer thickness. We recommend application of at least two layers. With the current state-of-the-art technical development, a permanent protection against algal and fungal infestation cannot be guaranteed.

#### **Further information**

Follow the instructions in the data sheets of the products used.



<sup>&</sup>lt;sup>2)</sup> Depending on needs, prime the gypsum plaster, gypsum plasterboard, gypsum wallboard with Lacryl Deep Penetrating Primer 595, Lacryl Hydro-Gel 695, Wall Primer 3729 or Wall Primer Coarse 3728.

This data sheet is based on extensive development work and years of practical experience. The translation corresponds to the current German version, in compliance with the German laws, regulations, standards and guidelines. Its content does not constitute a contractual legal relationship. The user/buyer is not released from the responsibility of checking our products to ensure they are suitable for the intended application. In addition, our general terms of business apply.

When a new version of this data sheet with updated information is published, the previous version no longer applies. The current version is available on our website.

Brillux Weseler Straße 401 48163 Münster GERMANY Phone +49 251 7188-0 Fax +49 251 7188-105 info@brillux.de www.brillux.com

