

## Floortec Aqua Hardener 812



Special epoxy hardener for Floortec 2C Aqua Basis 809 and Floortec 2C Aqua Thick Coat 810

### Field of application

For mixing with Floortec 2C Aqua Basis 809 and Floortec 2C Aqua Thick Coat 810.

### Properties

Special system hardener. The container size has been adapted to the mixing ratio.

### Material description

<b>Color shade</b>	Transparent
<b>Base material</b>	Epoxy resin
<b>Flash point</b>	+135°C
<b>Density</b>	Approx. 1.12 g/m <sup>3</sup>
<b>Packaging</b>	2 kg hardener for 20 kg of Floortec 2C Aqua Thick Coat 810 and 4 kg for Floortec 2C Aqua Basis 809 (base components and hardener in separate containers)

### Use

<b>Mixing</b>	Before adding the hardener, thoroughly stir the Floortec 2C Aqua Basis 809 and Floortec 2C Aqua Thick Coat 810 until even. Mix base component and hardener in the specified mixing ratio shortly before application. Ensure that the hardener container is completely emptied without residue. Follow the instructions in the Floortec 2C Aqua Basis 809 and Floortec 2C Aqua Thick Coat 810 data sheets.
<b>Compatibility</b>	Can only be mixed with materials specified in this data sheet.

## Use

**Application temperature** Do not apply at temperatures below +10°C or above a max. of +30°C air, substrate and material temperature. Take the dew point temperature into consideration. Do not apply unless the temperature is at least 3°C above the dew point. The relative humidity must not exceed 80%. The minimum temperature must also be ensured during curing.

**Tool cleaning** Clean tools immediately after use with water and wetting agent.

## Storage

Store in a cool, dry, and frost-free place. Reseal opened containers tightly.

## Declaration

**Product code** RE1  
Comply with the specifications in the current safety data sheet.

## Notes

**Further information** Follow the instructions on the data sheets of the products used.

## Remark

This data sheet is based on extensive development work and years of practical experience. The translation corresponds to the current German version, in compliance with the German laws, regulations, standards and guidelines. Its content does not constitute a contractual legal relationship. The user/buyer is not released from the responsibility of checking our products to ensure they are suitable for the intended application. In addition, our general terms of business apply.

When a new version of this data sheet with updated information is published, the previous version no longer applies. The current version is available on our website.

Brillux  
Weseler Straße 401  
48163 Münster  
GERMANY  
Phone +49 251 7188-0  
Fax +49 251 7188-105  
info@brillux.de  
www.brillux.com