

Floortec EP Hardener 849

Special epoxy hardener for Floortec 2K-EP Sealer 848 and Floortec 2K-EP Primer 473



Field of application

For mixing with Floortec 2K-EP Sealer 848 and Floortec 2K-EP Primer 473.

Properties

Special system hardener. The container size has been adapted to the mixing ratio.

Material description

Color shade	clear, yellowish
Base material	Water-dilutable epoxy resin
Flash point	+140°C
Density	Approx. 1.15 g/cm ³
Packaging	500 g hardener for 3 kg of Floortec 2K-EP Sealer 848 and 2 kg of Floortec 2K-EP Primer 473 1.67 kg hardener for 10 kg of Floortec 2K-EP Sealer 848 (base components and hardener in separate containers)

Use

Mixing	Before adding the hardener, thoroughly stir the Floortec 2K-EP Sealer 848 and Floortec 2K-EP Primer 473 until even. Mix base component and hardener in the specified mixing ratio shortly before application. Ensure that the hardener container is completely emptied without residue. Follow the instructions in the Floortec 2K-EP Sealer 848 and Floortec 2K-EP Primer 473 data sheets.
Compatibility	Can only be mixed with materials specified in this data sheet.

Use

Application temperature Do not apply at temperatures below +10°C or above a max. of +30°C air, substrate and material temperature. Take the dew point temperature into consideration. Do not apply unless the temperature is at least 3°C above the dew point. The relative humidity must not exceed 80%. The minimum temperature must also be ensured during curing.

Tool cleaning Clean tools with water and wetting agent immediately after use.

Storage

Store in a cool, dry and frost-free place. Reseal opened containers tightly.

Declaration

Product code RE20
Comply with the specifications in the current safety data sheet.

Notes

Further information Follow the instructions in the data sheets of the products used.

Remark

This data sheet is based on extensive development work and years of practical experience. The translation corresponds to the current German version, in compliance with the German laws, regulations, standards and guidelines. Its content does not constitute a contractual legal relationship. The user/buyer is not released from the responsibility of checking our products to ensure they are suitable for the intended application. In addition, our general terms of business apply.

When a new version of this data sheet with updated information is published, the previous version no longer applies. The current version is available on our website.

Brillux
Weseler Straße 401
48163 Münster
GERMANY
Phone +49 251 7188-0
Fax +49 251 7188-105
info@brillux.de
www.brillux.com