

2K-EP Varioprimer 865



Rust passivating adhesive primer, two-component, universally recoatable, for interior and exterior use

Field of application

As an adhesive primer for exterior and interior use, e.g., on zinc, galvanized steel, aluminum, copper pipes (heating pipes), coating plastics (BFS Leaflet No. 22), powder coatings, Coil Coating, Glasal, cement-bonded particle boards, melamine resin boards, wall tiles, load-bearing stove and two-component coatings, as well as on steel parts that are subject to high mechanical and chemical loads.

Properties

- Two-component
- Epoxy-resin-based
- Matt
- Rust passivating
- Extremely adhesion promoting
- Quick-drying
- Easy to apply
- For interior and exterior use
- High mechanical and chemical resistance
- Universally coatable with alkyd, acrylic, epoxy resin, PUR, polymerization paints

Material description

Colors	Scala No.	Description
	-	0095 white
	75.03.12	7035 light gray
	90.03.30	7126 anthracite
	27.12.24	8101 red brown

Basecode color shades can be mixed with the Brillux Color System.

Gloss grade Matt

Material description

Base material	Epoxy resin, solvent-based
VOC	EU limit value for this product (Cat. A/j): 500 g/l (2010). This product contains max. 500 g/l VOC. The specified VOC value refers to the ready-to-use mixture of base paint and hardener.
Flashpoint	+23°C
Density	Approx. 1.31 g/cm ³
Packaging	1 l combined container incl. hardener

Use

Mixing ratio	3.5 parts by volume 2K-EP Varioprimer 865 – component A – to 1 part by volume hardener – component B. This corresponds to approx. 5:1 parts by weight.
Mixing	Thoroughly mix the base paint and hardener in the specified mixing ratio. Then pour into another clean container and stir again thoroughly. Avoid inclusion of air during mixing. Do not mix freshly mixed material with residual material. Use the material immediately after the pre-reaction time, taking the pot life into account.
Pre-reaction time	After mixing, allow to pre-react for about 10 minutes.
Thinning	If necessary, thin up to a max. of 5% volume with Epoxy Thinner 854. Only thin after mixing and once the pre-reaction time has ended.
Tinting	All color shades can be mixed with one another.
Compatibility	Can only be mixed with similar materials and those stipulated in this data sheet.
Application	2K-EP Varioprimer 865 can be applied using brush, roller and spray application. This primer is preferably applied using a brush or roller. For spray application, we recommend using 2K-EP Varioprimer S 864.

Spray data

Spray system	Nozzle	Spray angle	Supply air/ air quantity	Material pres- sure/ material quantity	Thinning	Cross- spraying
high pressure	1.8 mm	–	–	3.5-4 bar	Approx. 5 %	1½
low pressure ¹⁾	yellow front end ²⁾	–	50–100%	Ring setting 6-8	Approx. 5 %	1–1½
airless ³⁾	0.008–0.012 inch	20°-50°	–	160 bar	Approx. 3%	1–1½

The data is based on substrate and ambient temperatures of +20°C

¹⁾ Information relating to XVLP technology with Wagner FinishControl FC 3500 or FC 5000.

²⁾ StandardSpray spray attachment (yellow) for all standard enamel paints and woodstains. Also keep the nozzle clean during application. Remove surface-dried paint material with a soft brush. Follow the equipment manufacturer's instructions.

³⁾ Information relating to the use of FineFinish nozzles 408, 410 and 412 (Trade tip 2/3 – violet) for, e.g., large-surface applications and nozzle 11/40 with otherwise unchanged settings.

Use

Pot life (at +20°C) Approx. 8 hours. Higher temperatures reduce pot life. After end of pot life, to not thin material again, do not use any-more.

Consumption Approx. 120 ml/m² of the ready-to-use mixture per coating. Determine exact consumption by means of a test application on the object to be coated.

Application temperature Do not apply at air and object temperatures below +8 °C and high humidity. An air and object temperature of +10 °C to +25 °C is ideal. Take the dew point temperature into consideration.

Tool cleaning Clean tools immediately after use with Epoxy Thinner 854

Drying (+20 °C, 65 % relative humidity)

Recoatable after approx. 6 hours. After 48 hours, a thorough sanding is required before recoating. Allow for longer drying time if the temperature is lower and/or the humidity is higher.

Storage

Store in a cool and dry place. Reseal opened containers tightly.

Declaration

Product code RE70
Comply with the specifications in the current Safety Data Sheet.

Coating build-up

Substrate preparation The substrate must be solid, dry, clean, with good adhesiveness, load-bearing, and free from separating agents. Check existing coatings for their suitability, load-bearing capacity, and adhesive properties. Prepare zinc, galvanized surfaces by cleaning them with Universal Cleaner 1032 or with ammonia alkaline washing fluid (in accordance with BFS Leaflet No. 5, Paragraph 3.3). Clean aluminum and bare metal with Universal Cleaner 1032 and non-woven abrasive, then rinse thoroughly with warm water. Clean anodized aluminum in a wet sanding procedure with, e.g., Universal Cleaner 1032 and wet sand paper – 240 grain or finer – and thoroughly rinse several times with warm water. When treating aluminum, follow the instructions in BFS Leaflet No. 6. Prepare plastics in accordance with BFS Leaflet No. 22. For substrates where there is a possibility of dissolving or peeling, for example, oil and enamel paint coatings, we recommend applying a test coat. Remove defective and unsuitable coatings completely, and dispose of them in accordance with the applicable regulations. Thoroughly sand intact old coatings. Hazardous particles and vapors may be released while reworking or removing old paint coats, e.g. as a result of sanding, paint removal by heat gun, etc. Perform such work only in well ventilated areas and ensure the use of appropriate protective equipment (including respiratory protective equipment) as required. Pretreat the substrate in accordance with the requirements. Also see VOB Part C, DIN 18363, Section 3.

Coating build-up

Prime coat	Depending on the type of structural component, requirement and choice, use 2K-EP Varioprimer 865. Always apply two prime coats on exterior zinc or zinc-coated surfaces if alkyd resin enamel paints are to be used for the subsequent top coat. Cement-bonded particle boards should be coated in a sufficient quantity and full covering on all sides, including the cut surfaces.
Intermediate and top coats	Depending on the component, requirement and selection, continue buildup with alkyd, acrylic, epoxy resin, PUR or polymerized resin paints.

Notes

Further recoating	In order to achieve good adhesion with the subsequent coating without sanding, the subsequent coat should be applied within 48 hours.
Interior application	Ensure proper ventilation during application and drying in interior areas.
Coating of horizontal, non-accessible surfaces	To thoroughly protect horizontal, non-accessible coated and absorbent surfaces such as concrete, e.g., balustrades, prime twice with 2K-EP Varioprimer 865. The horizontal concrete surfaces must be free of shrinkage cavities and have adequate surface inclination. Thin the first prime coat in accordance with the substrate absorption up to max. 5% with Epoxy Thinner 854. Additionally, scatter Floortec Quartz Sand 1526 onto the second, still-wet prime coat. Wait at least 12 hours between the individual prime coatings, but not more than 24 hours at the most.
Primer on Coil Coating	The suitability of Coil Coatings is to be evaluated on site on a case-by-case basis by means of a test coat.
Primer on wooden surfaces	For priming on wooden surfaces, we recommend using, e.g., Impredur Primer 835.
Implementation in brilliant and intense color shades	Brilliant, pure intense color shades, e.g., in the yellow, orange, red, magenta and yellow green areas have a lower hiding power as a result of the pigments used. For critical color shades, we recommend applying a full-covering base coat in these areas in the corresponding base color shade (Basecode). In addition to the standard coating buildup, additional coats may be required.
Further information	Follow the instructions in the data sheets of the products used.

Remark

This Data Sheet is based on extensive development work and years of practical experience. The translation corresponds to the current German version, in compliance with the German laws, regulations, standards and guidelines. Its content does not constitute a contractual legal relationship. The user/buyer is not released from the responsibility of checking our products to ensure they are suitable for the intended application. In addition, our general terms of business apply.

When a new version of this Data Sheet with updated information is published, the previous version no longer applies. The current version is available on our website.

Brillux
Weseler Straße 401
48163 Münster
GERMANY
Phone +49 251 7188-0
Fax +49 251 7188-105
info@brillux.de
www.brillux.com