

Decorative Molding Adhesive 3041

With high adhesive strength and good modeling characteristics, solvent-free



Field of application

For the professional and durable gluing of all Brillux Decorative Moldings 3040 as well as the Wallpaper Corner Profiles 3093 and 2095 in interior areas. On load-bearing substrates suitable for adhesives, e.g., interior plaster (compressive strength category CS II/CS III/CS IV and B1-B7), concrete, gypsum plasterboard, and intact coats of emulsion paint. Can also be used for fixing the TuneLight Aluminum profiles in the TL Decorative Moldings.

Properties

- For gluing and filling
- Good initial adhesion
- Good sanding and modeling properties
- Solvent-free
- Coatable

Material description

Color shade	white
Density	approx. 1.75 g/cm ³
Packaging	310 ml cartridge (approx. 525 g per cartridge)

Use

Substrate pretreatment The substrate must be solid, dry, clean, load-bearing, and free from efflorescence, sinter layers, separating agents, corrosion-promoting components, or other intermediate layers affecting the adhesion. Check existing coatings for their suitability, load-bearing capacity, and adhesive properties. Remove defective and unsuitable coatings thoroughly and dispose of them in accordance with the applicable regulations. Thoroughly wash off limepaint. Wash down intact oil and lacquer paint coats, sand down and clean thoroughly. Remove wall coverings, including paste residue and paper waste. Apply a prime and/or intermediate coat to the substrate as required. See also VOB Part C, DIN 18363, Section 3.

Verarbeitung

Application Apply an adequate amount of Decorative Molding Adhesive 3041 with a caulking gun onto the adhesion surfaces so that the adhesion surfaces are completely moistened after pressure has been applied to the moldings. Note that 2–3 mm of joint width are required for permanent butt joint bonding. For exceptions, please refer to the following note on the TL Decorative Moldings. Immediately remove adhesive residues with a moist sponge. Clean tools with water after use.

Note:

When mounting the TL Decorative Profiles for gluing on butt joints, it is essential to use Butt Joint Adhesive 3341.

Follow the instructions in the "Decorative Molding 3040" Data Sheet.

Open time
(+20°C, 65 % r. h.)

approx. 50–60 minutes. Rework filled joints, butt joints, etc. within this period.

Consumption

Approx. 37–42 ml/m (corresponds to approx. 7–8 m per cartridge).

The adhesive used depends on the Decorative Molding format.

Determine the exact consumption by means of a test application on the object to be coated.

Application temperature

Do not apply if air or object temperature is below +10 °C.

Tool cleaning

Clean with water immediately after use.

Drying (+20°C, 65% relative humidity)

Coatable after about 4–6 hours. The glue is completely dry after approx. 24 hours.

Allow longer drying times at lower temperatures and/or higher air humidity.

Storage

Cool and frost-free. Reseal opened containers tightly.

Declaration

Product code

Not assigned

Comply with the specifications in the current Safety Data Sheet.

Notes

Further information

Read and follow the instructions in the Data Sheets of the products to be used.

This Data Sheet is based on extensive development work and years of practical experience. The translation corresponds to the current German version, in compliance with the German laws, regulations, standards and guidelines. Its content does not constitute a contractual legal relationship. The user/buyer is not released from the responsibility of checking our products to ensure they are suitable for the intended application. In addition, our general terms of business apply.

When a new version of this Data Sheet with updated information is published, the previous version no longer applies. The current version is available on our website.

Brillux
Weseler Straße 401
48163 Münster
GERMANY
Phone +49 251 7188-0
Fax +49 251 7188-105
info@brillux.de
www.brillux.com