

Vitasense 9005



preservative-free, sustainable interior emulsion paint, dull matt, wet abrasion resistance R-class 1, good hiding power



Color System

Field of application

For high quality, preservative-free, sustainable wall and ceiling coats indoors, e.g. on interior plaster, concrete, gypsum plasterboard, fibrous cement, limestone brickwork. The material is particularly suited for renovation coatings, as only one coat is usually required thanks to the outstanding hiding power. Also suitable for larger surfaces with incidence of grazing light.

Properties

- Preservative-free, solvent-free and plasticizer-free
- low-emission
- Contains CO₂-reduced binder due to the use of renewable raw materials
- Filled in recycled containers
- Corresponds to requirements set out by "Ausschuss zur gesundheitlichen Bewertung von Bauprodukten" (AgBB, German Committee for Health-Related Evaluation of Building Products)
- Highly diffusible, complies with Class I in accordance with DIN EN ISO 7783
- Free of fogging-active substances
- Excellent hiding power
- Excellent surface results
- Long open time
- Particularly easy to apply
- For indoor use
- Suitable for allergy sufferers

Material description

- Color shades** 0095 white
A number of additional color shades can be mixed with the Brillux Color System while maintaining compliance with preservative-free properties.
- Base material** Polymer emulsion, titanium dioxide, calcium carbonate, silicates, polymer filler material, water and additives
- VOC** EU limit value for this product (Cat. A/a): 30 g/l (2010).
This product contains max. 1 g/l VOC.

Material description

Density	Approx. 1.5 g/cm ³
Classified in accordance with EN 13300	Wet abrasion resistance: R-class 1 Contrast ratio: H ₁₀ -class 1 (at 8 m ² /l) Gloss: G4 dull matt Maximum grain size: S1 fine
Water-vapor-permeability	Diffusion-equivalent air layer thickness: S _d (H ₂ O) < 0.1 m in accordance with DIN EN ISO 7783, corresponds to class V1 "high water vapor permeability" in accordance with DIN EN 1062-1
Reaction to fire	A2 – s1,d0 in accordance with DIN EN 13501-1 ("nichtbrennbar" non-combustible) In system build-up with Briplast filler material according to classification report no. 230010838-3
Packaging	5 l, 15 l

Use

Thinning	If necessary, thin slightly with water.
Tinting	Can be tinted with Full Color and Tinting Paint 951.
Compatibility	Can only be mixed with similar materials and those stipulated in this data sheet.
Application	Vitasense 9005 can be applied by using a brush, roller or airless spray application.
Consumption	Approx. 120–140 ml/m ² per layer. Determine the exact consumption by means of a test application on the object to be coated.
Application temperature	Do not apply if air or object temperature is below +5°C.
Tool cleaning	Clean tools with water immediately after use.

Spray data

Spray system	Nozzle	Spray angle	Pressure	Thinning
Airless	0.021–0.027 Inch	40°–80°	150 bar	Approx. 5%

Drying (+20 °C, 65 % relative humidity)

Surface dry and recoatable after approx. 4–6 hours.
Allow for longer drying time if the temperature is lower and/or the humidity is higher.

Storage

Sealed containers should be stored in a cool and frost-free place for up to 5 years. Reseal opened containers tightly and use material within a few days of opening.

Declaration

Notes Do not inhale spray mist

Product code BSW10
Comply with the specifications in the current safety data sheet.

Coating build-up

- Substrate preparation**
- The substrate must be solid, dry, clean, load-bearing and free from efflorescence, sinter layers, separating agents, corrosion-promoting components or other intermediate layers affecting the adhesion.
 - Check the suitability, load-bearing capacity and adhesive properties of existing coatings
 - Thoroughly remove defective and unsuitable coatings and dispose of them in accordance with the applicable regulations.
 - Thoroughly rinse off reversible, water-sensitive coats (e.g. distemper).
 - Wash down intact coats of oil paints and enamels with an alkaline solution, sand well and clean.
 - Completely remove any wall coverings that are not suitable for painting; this includes any paste or wall-glue residue.
 - Treat replastered areas with a fluorine primer; if the subsequent paint coat is to be tinted, prime the entire surface
 - See also VOB Part C, DIN 18363, Section 3.

First coats

Substrates	Prime coat	Intermediate coat	Top coat
Interior plaster ¹⁾ , concrete	If necessary, Vitabase 9002, Wall Primer 3729 or Wall Primer, coarse 3728	Vitasense 9005	Vitasense 9005
Gypsum plaster ¹⁾ , gypsum plasterboard ²⁾ , gypsum wallboard	Depending on the individual requirements Vitabase 9002, Wall Primer 3729 or Wall Primer, coarse 3728		
Aerated concrete, interior	Vitabase 9002		
Wall coverings, e.g. woodchip wallpaper, Rapid Nonwoven, embossed wallpaper			

¹⁾ Minimum compressive strength > 2.0 N/mm² (Compressive strength category CS II, CS III, CS IV as well as B1–B7).

²⁾ Prime soft and very absorbent filler zones and substrates with Vitabase 9002 as part of substrate preparation.

Renovation coatings

Substrates	Prime coat	Intermediate coat	Top coat
Normally absorbent substrates, e.g. matt emulsion paint coats	If necessary, Vitabase 9002, Wall Primer 3729 or Wall Primer, coarse 3728	Vitasense 9005 depending on the object and the requirements	Vitasense 9005
Non-absorbent or slightly absorbent substrates, e.g. oil and enamel paint coats, gloss emulsion paint coats	Adhesion Primer 3720		
Intact, two-component coating, e.g. CreaGlas 2K PU Finish 3471	2K-Aqua EP Primer 2373		

Notes

Filling rough surfaces

If necessary, smooth rough surfaces before the coating build-up by filling them with, e.g., Vitafill 9001 – preservative-free.

Hairline-crack-bridging coating on gypsum plasterboard

Hairline-crack-bridging coating on, e.g., gypsum plasterboard, gypsum fiber boards or similar substrates, in accordance with VOB Part C, DIN 18363, para. 3.2.1.2, can be achieved with full-surface reinforcement with, e.g., nonwoven wall coverings based on cellulose and fiberglass.

Discolorations on gypsum plasterboard

An additional sealing coating must be applied if there is a risk of discolorations bleeding through the untreated gypsum plasterboard. Depending on the situation on site, use Aqualoma 202, Isolating Primer 924 or CreaGlas 2K-PU-Finish 3471. For an accurate assessment, sample coatings of various panel widths, including the joints and filled areas, have proved to be useful.

Priming gypsum plaster

For gypsum-based plasters with strong absorbency, sufficient stabilization is not always achieved. We recommend testing the adhesion of the complete coating build-up with an adhesive tape test (e.g. Tesa Precision Masking Tape, Gold 4334) to ensure a reliable assessment. Where appropriate, implement priming with Deep Penetrating Primer.

Increased surface cleaning properties

To achieve a surface with higher cleanability (e.g. frequent, partial dirt removal with a damp cloth), we recommend using interior emulsion paints with wet abrasion resistance R-class 1 and a medium gloss or glossy surface.

Compatibility with sealing compounds

When coating sealing compounds e.g., acrylic sealing materials, due to higher elasticity, cracks can occur in the coating material. This may also cause discoloration in the coating. Due to the wide variety of sealing systems on the market, it is vital to perform tests for each individual case to assess the adhesion and application result.

Touch-ups	Touch-ups to part of a surface are always visible. The degree to which they stand out depends on the situation on site. According to BFS Leaflet no. 25, Section 4.2.2.1, Paragraph e, this is unavoidable.
Thin layers on smooth substrates	For thin-layer application to create low-texture surfaces on smooth substrates (e.g. filled gypsum plasterboard), additional coats may be required in order to achieve sufficient coverage or other measures may be required in the coating build-up. If necessary, contact the Brillux Consulting Service.
Projection surfaces	Due to the very white and matt surface, also suitable as a coating for projection surfaces (without determining the gain factor).
Further information	Follow the instructions on the data sheets of the products used.

Remark

This data sheet is based on extensive development work and years of practical experience. The translation corresponds to the current German version, in compliance with the German laws, regulations, standards and guidelines. Its content does not constitute a contractual legal relationship. The user/buyer is not released from the responsibility of checking our products to ensure they are suitable for the intended application. In addition, our general terms of business apply.

When a new version of this data sheet with updated information is published, the previous version no longer applies. The current version is available on our website.

Brillux
Weseler Straße 401
48163 Münster
GERMANY
Phone +49 251 7188-0
Fax +49 251 7188-105
info@brillux.de
www.brillux.com