## **Radiator Enamel 990**

aromatics-free, good hiding power, high gloss, heat-resistant up to  $+180^{\circ}\text{C}$ 





Color System

Field of application		
	For hard-wearing coats on steel and cast iron radiators, powder coated radiators as well as pipelines in warm water and steam heating systems. Also suitable for use in green houses.	
Properties		
	<ul> <li>Aromatics-free</li> <li>Based on alkyd resin</li> <li>High gloss</li> <li>Heat-resistant up to +180 °C</li> <li>adhesive</li> <li>good hiding power</li> <li>very hard-wearing</li> <li>with good flow properties</li> <li>low yellowing tendency</li> <li>excellent edge coverage</li> <li>Complies with EN 71-3 Safety of toys, resistant to saliva and perspiration</li> <li>easy to apply</li> </ul>	
Material description		
Colors	0095 white Light color shades can be mixed using the Brillux Color System	
Gloss grade	high-gloss	
Base material	Alkyd resin, solvent-based, pigmented	
VOC	EU limit for this product (Kat. A/i): 500 g/l (2010) This product contains a max. of 500 g/l VOC	
Flash point	+41 °C	
Density	approx. 1,13 g/cm³	
Packaging	Standard: 375 ml, 750 ml, 3 l	



Use	
Thinning	Ready for use. Do not thin, oth-erwise the EU limit according to VOC directive is exceeded.
Tinting	No tinting. Light color shades are mixable using the Brillux Color System. For medium or full tinted coats on hot water radiators up to a max. of +80 °C, use Impredur High Gloss Enamel 840 or Im-predur Silk Matt Enamel 880 (except for all light color shades).
Compatibility	May only be mixed with materials of the same type and the materials specified for this purpose in this data sheet.
Application	Radiator Enamel 990 can be ap-plied by means of paintbrush or paint roller.
Consumption	Approx. 80 to 100 ml/m <sup>2</sup> per layer. Determine exact consumption by means of a test application on the object to be coated.
Application temperature	Do not apply if air or object temperature is below +5°C.
Tool cleaning	Clean tools immediately after use with Thinner AF 631 or Quick-Acting Brush Cleaner 111.
Drying (+20 °C, 65 % relative hum	idity)
	Dust-dry after approx. 3 hours. Recoatable after approx. 24 hours. Allow longer drying times at lower temperatures and/or higher air humidity.
Storage	
	Store in a cool and dry place. Reseal opened containers tightly.
Declaration	
Product code	BSL20 Comply with the specifications in the current safety data sheet.



Substrate preparation	The substrate must be solid, dry, clean, with good adhesiveness, load- bearing and free from separating agents. Remove rust from iron and damaged areas. Check existing coatings for their suitability, load- bearing and adhesive properties. Remove defective and unsuitable coatings and dis-pose of them in accordance with the applicable regulations. Thoroughly sand intact coats. Hazardous particles and vapors can be released while working on or removing coats, e.g. by means of sanding, flame cleaning, etc. Perform such work only in well ventilated areas and ensure the use of appropriate (breathing) protection as required. Depending on the requirements pretreat the sub- strate, apply a prime and/or intermediate coat. Also see VOB Part C, DIN 18363, Section 3.
-----------------------	---

Substrates	Prime coat	Intermediate and top coat	
radiators, pipelines, etc, interior, untreated or paint stripped	Metal Primer 850		
radiators, pipelines, etc, interior, factory primed	defective areas with		
Radiators, pipelines, etc, interior, with intact load- bearing alkyd resin paint	Metal Primer 850	depending on the requirements once or twice Radiator Enamel 990	
Radiators with intact stoving enamel coat, powder coat and untreated non-ferrous metal pipelines interior	2K-Epoxi Varioprimer 865 or 2K- Epoxi Vario-primer S 864		

Coats an	radiators	and	radiator	pipelines
----------	-----------	-----	----------	-----------

Notes			
Factory priming	Factory priming must comply with DIN 55900.		
Large-surface applications	For large-surface applications, we recommend using the waterbased LacryI-PU Radiator Enamel 265 due to the typical smell of solvent- based alkyd res-in paints.		
Sanding surfaces	We recommend sanding the surfaces between the individual work steps. Light sanding is required in particular if a "coat-on-coat" structure is used.		
Heating-up radiators	We recommend heating up the radiators immediately after painting to minimize the odor build up and to facilitate faster drying.		
Further information	Follow the instructions on the data sheets of the products used.		



This Data Sheet is based on extensive development work and years of practical experience. The translation corresponds to the current German version, in compliance with the German laws, regulations, standards and guidelines. Its content does not constitute a contractual legal relationship. The user/buyer is not released from the responsibility of checking our products to ensure they are suitable for the intended application. In addition, our general terms of business apply.

When a new version of this Data Sheet with updated information is published, the previous version no longer applies. The current version is available on our website.

Brillux Weseler Straße 401 48163 Münster GERMANY Phone +49 251 7188-0 Fax +49 251 7188-105 info@brillux.de www.brillux.com

